

SPECIFICATIONS

Commercial	1200 - Obsolete

Applications:

Metal work, license plates, identification plates. Kitchenware, packaging foils, containers, automotive trim, heat exchanger strip, radiator tubes. Aircraft and military highly stressed structures.

Characteristic Properties:

Very good atmospheric corrosion resistance and workability. High thermal conductivity and reflectivity but lower than for 1050A. Very good weldability. Slightly higher strength than 1050A.

CHEMICAL COMPOSITION

BS 5L34(1985) Alloy L34	
Element	% Present
Aluminium (AI)	99 min
Silicon + Iron (Si+Fe)	1 max
Others (Total)	0.15 max
Zinc (Zn)	0.1 max
Titanium (Ti)	0.05 max
Manganese (Mn)	0.05 max
Copper (Cu)	0.05 max
Other (Each)	0.05 max

Cast billets & slabs for hot working and extruded bars, sections and hot-rolled plate for forging shall be supplied non-heat treated.

Bars for machining & extruded sections shall be supplied in one of the following conditions:

Extruded;

Extruded & Drawn:

Rolled & Drawn

and subsequently straightened.

Forgings, unless otherwise agreed in accordance with BS L100, shall be supplied as forged or annealed.

No heat treatment is required.

ALLOY DESIGNATIONS

Aluminium alloy 5L34 - 1200 is covered by Standard BS EN 5L34 (1985) - Now Obsolete.

TEMPER TYPES

The most common tempers for 5L34 - 1200 aluminium are as forged 'F' or fully annealed 'O'

- F As fabricated
- 0 Soft

SUPPLIED FORMS

5L34-1200 aluminium is supplied as forging stock and forgings made from cast billet, extruded stock or rolled plate

- Bar
- Extrusions
- Forgings
- Plate
- Castings

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.59 g/cm ³
Melting Point	657 °C
Thermal Expansion	23.4 x10 ⁻⁶ /K
Modulus of Elasticity	69 GPa
Thermal Conductivity	225 W/m.K
Electrical Resistivity	58.5 % IACS

MECHANICAL PROPERTIES

BS 5L34(1985)		
Property	Value	
Tensile Strength	65 Min MPa	
Elongation A50 mm	18 Min %	

The specification covers forging stock, bars, extruded sections and forgings of 99% aluminium.

This specification was declared obsolescent on 01 April 1999. It is no longer recommended for use on new designs.







CONTACT

Address: (incorporated in the USA)
Tel: +44 (0)1371 811 642
Email: info@aerometalsalliance.com

REVISION HISTORY

Datasheet Updated 07 January 2014

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.

[2 OF 2]







