

SPECIFICATIONS

Commercial	2024 CLAD 1050A
------------	-----------------

Applications:

High strength fabricated or machined items in aircraft industries, general engineering, machinery, military equipment, truck wheels. Screw machine products. Structural applications. Rivets.

Characteristic Properties:

Heat treatable alloy. Very good machining characteristics. High strength alloy with a strength slightly higher than 2014(A) and 2017A and 2030. High fatigue strength. Suitable for welding only by resistance welding. Corrosion resistance only with cladding or other protection.

CHEMICAL COMPOSITION

BS L109(1971) Alloy L109	
Element	% Present
Copper (Cu)	3.8 - 4.9
Magnesium (Mg)	1.2 - 1.8
Manganese (Mn)	0.3 - 0.9
Iron (Fe)	0.5 max
Silicon (Si)	0.5 max
Zinc (Zn)	0.2 max
Titanium + Zirconium (Ti+Zr)	0.2 max
Chromium (Cr)	0.1 max
Nickel (Ni)	0.05 max
Lead (Pb)	0.05 max
Tin (Sn)	0.05 max
Aluminium (Al)	Balance

Heat Treatment:

Material shall be supplied solution treated, straightened and aged at room temperature.

Material shall be heat treated as follows:

1. Solution treat by heating at a temperature of 495 +/- 5C and quenching in water at a temperature not exceeding 40C.
2. Age at room temperature for not less than 48 hours.

ALLOY DESIGNATIONS

Aluminium alloy L109 - 2024 clad 1050A is covered by standard BS L109 (1971)

TEMPER TYPES

The most common temper for L109 - 2024 clad 1050A aluminium is:

- T4 - Solution heat treated and naturally aged to a substantially stable condition

SUPPLIED FORMS

L109 - 2024 CLADd 1050A aluminium is as sheet and strip

- Sheet
- Strip

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.79 g/cm ³
Melting Point	640 °C
Thermal Expansion	23.1 x10 ⁻⁶ /K
Modulus of Elasticity	73 GPa
Thermal Conductivity	121-193 W/m.K

MECHANICAL PROPERTIES

BS L109(1971) Sheet 0.4mm to 0.8mm	
Property	Value
Elongation A50 mm	12 Min %
Tensile Strength	405 Min N/mm ²
Elongation A	%
0.2% Proof Stress	270 Min N/mm ²

This specification covers aluminium-coated sheet and strip of aluminium-copper-magnesium-manganese alloy.

The cladding material shall comply with the international designation 1050A.

Mechanical property values relate to material with a nominal thickness of 0.4 up to and including 0.8mm. This specification contains other values for different material thicknesses.

CONTACT

Address:	(incorporated in the USA)
Tel:	+44 (0)1371 811 642
Email:	info@aerometalsalliance.com

REVISION HISTORY

Datasheet Updated	09 January 2014
-------------------	-----------------

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.