

SPECIFICATIONS

Commercial	7075 - OBSOLETE
------------	-----------------

Applications:

Aircraft and military highly stressed structural components. Rolling stock for machine parts and tools (for rubber and plastics). Screws and bolts, nuts. Rivets. Nuclear applications.

Characteristic Properties:

Heat treatable very high strength alloy with a strength slightly lower than 7010. Very high fatigue strength. Joining preferably by rivets, adhesives or screws. Corrosion protection is recommended also in outdoor atmosphere.

Precautions and Warnings:

Care to be taken when selecting temper (and other thermal treatment) for balance of properties. May be clad with 7072 for better protection against stress corrosion cracking.

CHEMICAL COMPOSITION

BS 2L95(1971)
Alloy L95

Element	% Present
Zinc (Zn)	5.1 - 6.4
Magnesium (Mg)	2.1 - 2.9
Copper (Cu)	1.2 - 2
Iron (Fe)	0.5 max
Silicon (Si)	0.4 max
Manganese (Mn)	0.3 max
Chromium (Cr)	0.1 - 0.25
Titanium + Zirconium (Ti+Zr)	0.2 max
Others (Total)	0.15 max
Other (Each)	0.05 max
Tin (Sn)	0.05 max
Nickel (Ni)	0.05 max
Lead (Pb)	0.05 max
Aluminium (Al)	Balance

ALLOY DESIGNATIONS

Aluminium alloy L95 - 7075 is covered by standard BS 2L95 (1971). BS2L95 (1971) was superseded by BS EN 2126 on 15 October 1996.

TEMPER TYPES

The most common temper for L95 - 7075 aluminium is:

- T651 - Solution heat treated, stress relieved by stretching then artificially aged

SUPPLIED FORMS

L93 - 7075 aluminium is supplied in Plate

- Plate

GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.81 g/cm ³
Melting Point	635 °C
Thermal Expansion	23.5 x10 ⁻⁶ /K
Modulus of Elasticity	72 GPa
Thermal Conductivity	134-160 W/m.K
Electrical Resistivity	40 % IACS

'Typical' Physical Properties are given

MECHANICAL PROPERTIES

These Mechanical properties are for Plate in the T651 temper

Thickness (mm)	Proof Strength (Min)	Tensile Strength (Min)	Elongation % (Min)
Over 6 to & incl. 12.5	450	530	8
Over 12.5 up to & incl. 25	450	530	6
Over 25 up to & incl. 40	450	530	5
Over 40 up to & incl. 63	440	510	5
Over 63 up to & incl. 90	410	500	5

CONTACT

Address:	(incorporated in the USA)
Tel:	+44 (0)1371 811 642
Email:	info@aerometalsalliance.com

REVISION HISTORY

Datasheet Updated	09 January 2014
-------------------	-----------------

DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.